

# Quality Certificate

Quality reference **1600.11 | CHENILLE**  
 Category **Woven Chenille**  
 Composition **100% Inherent FR polyester**  
 Weight **400 g/m<sup>2</sup> | 11.80 oz/yd<sup>2</sup>**  
 Width **138-140 cm**  
 Piece length **± 45 m | 49 yd**  
 Dye batch length **± 180 m | 196 yd**  
 Features **Recyclable after-use | 148 in-stock colours | cut length service**

TEST	PRODUCT STANDARD: EN 14465		REQUIREMENTS	RESULTS
<b>Breaking strength</b>	ISO 13934-1	Warp	min. 400 N	<b>1500 N</b>
		Weft	min. 400 N	<b>940 N</b>
<b>Tear resistance</b>	EN ISO 13937-3	Of the warp	min. 30 N	<b>40 N</b>
		Of the weft	min. 30 N	<b>41 N</b>
<b>Seam slippage</b>	ISO 13936-2	Warp	max. 5mm	<b>1.00 mm</b>
		Weft	max. 5mm	<b>1.00 mm</b>
<b>Abrasion resistance</b>	ISO 12947-2	Colour degradation at 3000 rubs	min. 3	<b>4</b>
		Complete wear out	min. 25.000 rubs	<b>35.000 rubs</b>
<b>Colour fastness to light</b>	EN ISO 105 B02	Colour	min. 5	<b>5 - 6</b>
<b>Colour fastness to rubbing</b>	EN ISO 105-X12	Dry	min. 3-4	<b>4 - 5</b>
		Wet	min. 3	<b>4 - 5</b>
<b>Fastness to water</b>	EN ISO 105-E01	Colour	min. 3	<b>4</b>
<b>Dimensional change in domestic washing and drying</b>	EN ISO 5077	Warp	max. 3%	<b>0.3 %</b>
	EN ISO 6330	Weft	max. 3%	<b>0.3 %</b>

**COLOUR MATCHING:** Whilst every effort has been made to ensure that colours correspond closely to those illustrated in our pattern range, we cannot guarantee to match the samples exactly.

